

Ball Clay

BC-3 & BC-8

- **Application:** sanitary ware.
- **Specification:**

Item (%)		BC-3	BC-8
SiO ₂		52.98	56.68
Al ₂ O ₃		30.58	28.34
Fe ₂ O ₃		1.79	1.83
TiO ₂		0.71	0.51
CaO		0.15	0.23
MgO		0.36	0.05
K ₂ O		0.87	1.24
Na ₂ O		0.01	0.39
L.O.I		12.24	10.58
Moisture		19±1	19±1
Firing whiteness	1190°C	56.4	54.3
L.O.I	1190°C	12.2	10.4
Shrinkage	1190°C	5.0	7.2

Country of Origin: China