

**KAOLIN CLAY**

OG-71

➤ **Specification (%):**

Test date: January 19, 2017

Report date: January 22, 2017

<b>Spec.</b>	<b>Model</b>	<b>OG-71</b>
	<b>SiO<sub>2</sub></b>	51.72
	<b>Al<sub>2</sub>O<sub>3</sub></b>	35.41
	<b>Fe<sub>2</sub>O<sub>3</sub></b>	0.37
	<b>CaO</b>	0.20
	<b>MgO</b>	0.21
	<b>K<sub>2</sub>O</b>	0.11
	<b>Na<sub>2</sub>O</b>	0.03
	<b>TiO<sub>2</sub></b>	0.02
	<b>Ig. Loss</b>	11.83
	<b>Natural Whiteness</b>	75.8
	<b>Firing Whiteness (1280°C)</b>	90.4
	<b>Moisture, %</b>	24±1
	<b>Particle Size</b>	2µm passing: ≥69.00 <74.00

**Country of Origin: China**