

Kaolin Ore C (Ceramic Grade)

Edition: Rev D 25/05/2019

Chemical Property**	Value (%)
*SiO ₂	46.5
Al ₂ O ₃	39.6
Fe ₂ O ₃	0.08
TiO ₂	0.15
K ₂ O	0.25
Ig. Loss	13.2

Physical Property	Value
Product Form	Run of Mine Matrix @ nominal 12% moisture, < 45µm Kaolin content ~ 50% (dry basis)
Fired ISO Brightness (%)	>90
Particle Size Distribution (Sedigraph %) (<45µm fraction before any sizing or attrition)	
Mass passing 2µm	45

The above data are typical average data for the product and should not be treated as absolute specification.

Country of Origin: Australia